



TURMOTEMP LP 5002

K P FK 2 U -30



Date of issue: 28.10.2015

TURMOTEMP LP 5002 is a special grease for the lubrication of highly loaded rolling bearings.

TURMOTEMP LP 5002 is a special grease based on perfluorinated polyethers (PFPE) and a special lithium soap. Due to this we were able to combine the positive properties of the chemically and thermally very stable perfluorinated base oils with the excellent properties of the metal soaps. This means under thermal and mechanical load the lubricant flows back to the contact surfaces and reduces wear to a minimum.

The preferred service temperature range is > 120°C to 250°C.

Special properties

- High load carrying capacity
- Excellent corrosion and wear protection
- High temperature stability
- Good media resistance
- Miscible with all PFPE/PTFE containing lubricants

Product Characteristics	Value	Dimension	Norm / Standard
Colour	light beige		
Density at 20°C	1,73	g/cm ³	DIN 51757
Operating temperature range	-30 to 250	°C	
Thickener	Lithium special soap		
Base oil	PFPE		
Kin. viscosity of the base oil at 40°C	500	mm ² /s	DIN EN ISO 3104
Kin. viscosity of the base oil at 100°C	46	mm ² /s	DIN EN ISO 3104
Worked penetration	265 – 295	mm/10	DIN ISO 2137
Consistency class (NLGI)	2		DIN 51818
Dropping point	> 250	°C	DIN ISO 2176
Resistance to water	0 – 90		DIN 51807
Corrosion protection (SKF-Emcor)	0 / 0		DIN 51802
Speed factor of grease (n x dm)	250 000	mm/min	
Four-ball test O.K. load / welded load	5500 / 6000	N	DIN 51350

Application

Preferred application areas include long-term spherical roller bearings, cylindrical roller bearings and taper roller bearings at high temperatures. Chain return wheels and return roller bearings subject to high temperatures, load rollers in film stretching machines and textile stenters as well as low speed electric motors.

Before applying **TURMOTEMP LP 5002** all lubricating points should be cleaned carefully. Optimum lubricating properties can only be fully achieved on clean and dry material surfaces.

Special cleaning agents which must be used for PFPE-lubricants thickened with PTFE, are not required.

Packaging units

170 g tubes, 700 g cartridges, 1 kg cans, 5 kg bucket, 10 kg bucket, 25 kg hobbock

The products are subject to continuous strict production controls and comply with our own factory specifications. A warranty for each case cannot be given, due to the variety of relevant factors. Therefore, we recommend the implementation of field tests. Herewith, any liability is expressly excluded.

LUBRICANT CONSULT GMBH · Gutenbergstrasse 13 · 63477 Maintal (Germany)

Tel: +49 (0) 6109 / 7650-0 · Fax: +49 (0) 6109 / 7650-51 · E-Mail: webmaster@lubcon.com · Internet: <http://www.lubcon.com>